












## TECHNICAL INFORMATION / TEKNISK INFORMATION



# BERGO TENNIS

Material:		ISO2076	Environmentally friendly recyclable/ Miljövänlig återvinningsbar UV-stabilized polypropylene. UV-stabiliserad polypropen.
Size of tile: /Plattans storlek:		EN427	301,6 x 301,6 mm. 1 m <sup>2</sup> / box = 11 tiles. 5 m <sup>2</sup> / box = 55 tiles. 1,09 m <sup>2</sup> /sheet = 4x3 tiles.
Thickness of tile: /Plattans tjocklek:		EN428	13,3 mm.
Weight: /Vikt:		EN430	1 tile: 0,3 kg. 5 m <sup>2</sup> : 17,1 kg (Maxi-pack) 4x3 tiles: 3,6 kg (Preassembled sheets)
Point load: /Punktbelastning:		QUALIFIED TEST BY BERGO	550 ton / 1 m <sup>2</sup> = 5500 kg/dm
Light fastness: /Ljusbeständighet:		EN 14836 (>3) ISO 105-B02 (1-8) ISO 105-A02 (>0,3)	4-5 7-8 4/5
Weather Fastness /UV- Florida test (1-5):		ASTM D1435 ASTM G154 Cycle A	4/5
Slip resistance: /Halkmotstånd:		SSEN-13893 EN13036-4	>0,3 96 PTV
Impact resistance: /Slagtålighet:		ISO179/1eA ASTM D746	+23 °C = 20 kJ/m <sup>2</sup> / -20 °C = 5 kJ/m <sup>2</sup> C 15 kJ/m <sup>2</sup>
Fire category /Brandklassning:		EN ISO 11925-2	E <sub>fl</sub>
CE certification:		EN 14041	0402-CPD-P605080A
Shock absorption: /Stötupptagning		EN 14808	6 %
Vertical deformation: /Svikt		EN 14809	0,3 mm
Vertical ball behaviour: /Bollstud		EN 12235	102 %
Resistance to wear: /Nötningsmotstånd		EN ISO 5470-1	0,1 g / 1000 cycles
Water infiltration rate: /Vattengenomsläpplighet		EN 12616	Requirement very well achieved. /Uppfyller kraven med god marginal.
Court pace Classification: /Hastighetsklassificering		ITFCS01/02-09-013	Category 5 - fast.

### EXPLANATION OF EXPANSION IN VARIOUS TEMPERATURES/ FÖRKLARING TILL UTVIDGNING I OLIKA TEMPERATURER

Expansion: 0,15 % per 10 °C

Formel för själva expansionens (utvidgnings) storlek: (0,0015 x längden av golvet) x (temperaturökning ( i grader)/10)

Formula for the size of the expansion: (0,0015 x length of the floor) x (number of increased degrees /10)

Formula for the length of the floor after the expansion: Earlier length + Length of the expansion

Example Exempel	Length of floor Längd på golvet	Calculation Uträkning	Expansion	Length of floor after expansion Längd på golvet efter expansion
0°C–10°C	10 m	0,0015 x 10m = 0,015m 0,015m x (10°/10) = 0,015	1,5 cm	10,015 m
0°C–30°C	10 m	0,0015 x 10m = 0,015m 0,015m x (30°/10) = 0,045	4,5 cm	10,045 m
20°C–40°C	20 m	0,0015 x 20m = 0,030m 0,030m x (20°/10) = 0,06	6,0 cm	20,06 m




By normal use and treatment the material guarantee time is 10 years.



Bergo Flooring AB fulfills the requirements of ISO 9001.



Bergo Floors are 100% recyclable.



The Bergo Tile - Polypropylene floor covering for use out- and indoors. Reaction to fire Class Efl. Slipperiness DS.



www.bergoflooring.com

